

Buna SE VP PBR 4022

Product Description

Buna SE VP PBR 4022 is a butadiene-styrene copolymer, produced by cold emulsion polymerization, using fatty and rosin soaps as emulsifiers. The monomers are randomly distributed in the polymer structure, while the butadiene fraction is found in its major part in the trans configuration with small fractions of cis and vinyl configurations.

CAS No.: 9003-55-8.

The rubber is protected by a staining stabiliser system and extended with Nytex 4700 oil which is compliant with the European directive 2005/69/EC.

This is a trial product and therefore the nominal values given are temporary and subject to change.

Production plant: Duque de Caxias -RJ - Brazil

Supply Form

Dark rubber bales wrapped in polyethylene foil.

Raw Material Properties

Property	Nominal Value	Unit	Test Method
Volatile Matter	max. 0.5	% by wt	ASTM D 5668
Mooney Viscosity	50	ME	ASTM D 1646
Free soap	max. 0.5	% by wt	ASTM D 5774
Organic acid	5.1	% by wt	ASTM D 5774
Bound styrene	23.5	% by wt	ASTM D 5775
Oil content	27.2	% by wt	ASTM D 5774

Other Product Features

Property	Typical Value
Density	0,94 g/cm ³
trans-1,4	75% by wt
cis-1,4	10% by wt
vinyl content	15% by wt



Buna SE VP PBR 4022

Use	Buna SE VP PBR 4022 is used where there is a need for low cost together with resistance to wear and tear, resistance to cracking and excellent processing conditions. It processes easily in extrusion and calendering. It is used in tires, retread, conveyor belts, piping, hoses, tubings, carpets, moulded products in general and shoe soles.		
Solubility	Buna SE VP PBR 4022 rubber is soluble in aliphatic hydrocarbons, styrene, toluene, tetrahydrofurane, cyclohexane, methylene chloride and 1,1,1-trichloroethane, and is insoluble in alcohols and water.		
Storage Life/Conditions	Buna SE VP PBR 4022 should be stored in its original packaging in a cool, dry place at temperatures below 40°C. Exposure to light must be avoided and also other heat sources. Under suitable conditions the product is stable for 12 months.		
Packaging	Bale weight	35	kg
	Nominal crate weight	1260	kg
Marking	Grade / Lot number / Crate number / Net weight		
Product Safety	Literature on the health and safety aspects of this product has been published. Before working with this product, personnel must be familiarised with its hazards, proper use, and handling. The available information is summarised in the Safety Data Sheet.		

These raw material properties are typical and, unless specifically indicated otherwise, are not to be considered as delivery specification.

Buna SE VP PBR 4022

Health and Safety Information: Appropriate literature has been assembled which provides information concerning the health and safety precautions that must be observed when handling the LANXESS products mentioned in this publication. For materials mentioned which are not LANXESS products, appropriate industrial hygiene and other safety precautions recommended by their manufacturers should be followed. Before working with any of these products, you must read and become familiar with the available information on their hazards, proper use and handling. This cannot be overemphasized. Information is available in several forms, e.g., material safety data sheets, product information and product labels. Consult your LANXESS representative in Germany or contact the Health, Safety, Environment and Quality Department (HSEQ) of LANXESS Germany or - for business in the USA - the LANXESS Product Safety and Regulatory Affairs Department in Pittsburgh, PA.

Regulatory Compliance Information: Some of the end uses of the products described in this publication must comply with applicable regulations, such as the FDA, BfR, NSF, USDA, and CPSC. If you have any questions on the regulatory status of these products, contact your LANXESS Corporation representative, the LANXESS Regulatory Affairs Manager in Pittsburgh, PA or the Health, Safety, Environment and Quality Department (HSEQ) of LANXESS Deutschland GmbH in Germany.

The manner in which you use and the purpose to which you put and utilize our products, technical assistance and information (whether verbal, written or by way of production evaluations), including any suggested formulations and recommendations are beyond our control. Therefore, it is imperative that you test our products, technical assistance and information to determine to your own satisfaction whether they are suitable for your intended uses and applications. This application-specific analysis must at least include testing to determine suitability from a technical as well as health, safety, and environmental standpoint. Such testing has not necessarily been done by us. Unless we otherwise agree in writing, all products are sold strictly pursuant to the terms of our standard conditions of sale. All information and technical assistance is given without warranty or guarantee and is subject to change without notice. It is expressly understood and agreed that you assume and hereby expressly release us from all liability, in tort, contract or otherwise, incurred in connection with the use of our products, technical assistance, and information.

Any statement or recommendation not contained herein is unauthorized and shall not bind us. Nothing herein shall be construed as a recommendation to use any product in conflict with patents covering any material or its use. No license is implied or in fact granted under the claims of any patent.

Issue number: Buna SE VP PBR 4022 / Date of issue: January 26, 2009 / Information current as of date of issue.
Please contact your LANXESS representative to determine if this publication has been revised.