

Buna CB VP PBR 4037

Product Description

Buna CB VP PBR 4037 is a solution medium cis polybutadiene polymer produced with an organo lithium catalyst. CAS No.: 9003-17-2
The rubber is protected by a stabiliser system which is in chemical compliance with the FDA regulation §177.1640, the recommendation VI of the Federal Institute for Risk Assessment and the Commission Directive 2002/72/EC respectively its further amendments including 2004/19/EC.

Plant : Pt. Jérôme

This is a trial product and therefore the nominal values given are temporary and subject to change.

Supply Form

Rubber bales wrapped in polystyrene foil.

Raw Material Properties

Property	Nominal Value	Unit	Test Method
Volatile matter	max. 0,75	% by wt	MO AQ 255 LAB
Mooney Viscosity	54	ME	ASTM D 1646
Solution viscosity (5,43% in toluene)	163	mPa·s	MO AQ 272 LAB
styrene insoluble (wet gel)	max. 150	ppm	MO AQ 259 LAB
Colour Yellowness Index(Bulk rubber)	max. 4,5		MO AQ 502 LAB

Other Product Features

Property	Typical Value
ash content	max. 0,2 % by wt
amount of stabiliser	min. 0,65 % by wt
vinyl content	11% by wt
cis 1,4 content	38 % by wt
trans 1,4 content	51 % by wt

Buna CB VP PBR 4037

Use	Buna CB VP PBR 4037 is used for the production of ABS and HIPS. For HIPS it is used either alone or in blend with BUNA CB 565 T or with SB-Polymers to achieve polystyrene with improved surface gloss. In blends with Buna CB 530 T it is possible to attain an improved stress cracking resistance.		
Solubility	Buna CB VP PBR 4037 rubber is soluble in aliphatic hydrocarbons, styrene, toluene, tetrahydrofurane, methylene chloride, 1,1,1-trichloroethane and cyclohexane, and is insoluble in alcohols and water.		
Packaging	Bale weight	33,0 +-0,6	kg
	Nominal bale size	71 x 35 x 17	cm
	Nominal crate weight	~1188	kg
	Crate size	1465x1150x1098	mm
Storage Life/Conditions	Buna CB VP PBR 4037 should be stored in a cool, dry place at temperatures below 35°C. Exposure to light must be avoided. Under suitable conditions the product is stable for 12 months.		
Marking	Grade / Lot number / Crate number / Net weight		
Product Safety	Literature on the health and safety aspects of this product has been published. Before working with this product, personnel must be familiarised with its hazards, proper use, and handling. The available information is summarised in the Safety Data Sheet.		

These raw material properties are typical and, unless specifically indicated otherwise, are not to be considered as delivery specification.

Buna CB VP PBR 4037

Buna CB for plastic modification is a Registered Trademark of LANXESS Deutschland GmbH

Health and Safety Information: Appropriate literature has been assembled which provides information concerning the health and safety precautions that must be observed when handling the LANXESS products mentioned in this publication. For materials mentioned which are not LANXESS products, appropriate industrial hygiene and other safety precautions recommended by their manufacturers should be followed. Before working with any of these products, you must read and become familiar with the available information on their hazards, proper use and handling. This cannot be overemphasized. Information is available in several forms, e.g., material safety data sheets, product information and product labels. Consult your LANXESS representative in Germany or contact the Health, Safety, Environment and Quality Department (HSEQ) of LANXESS Germany or - for business in the USA - the LANXESS Product Safety and Regulatory Affairs Department in Pittsburgh, PA.

Regulatory Compliance Information: Some of the end uses of the products described in this publication must comply with applicable regulations, such as the FDA, BfR, NSF, USDA, and CPSC. If you have any questions on the regulatory status of these products, contact your LANXESS Corporation representative, the LANXESS Regulatory Affairs Manager in Pittsburgh, PA or the Health, Safety, Environment and Quality Department (HSEQ) of LANXESS Deutschland GmbH in Germany.

The manner in which you use and the purpose to which you put and utilize our products, technical assistance and information (whether verbal, written or by way of production evaluations), including any suggested formulations and recommendations are beyond our control. Therefore, it is imperative that you test our products, technical assistance and information to determine to your own satisfaction whether they are suitable for your intended uses and applications. This application-specific analysis must at least include testing to determine suitability from a technical as well as health, safety, and environmental standpoint. Such testing has not necessarily been done by us. Unless we otherwise agree in writing, all products are sold strictly pursuant to the terms of our standard conditions of sale. All information and technical assistance is given without warranty or guarantee and is subject to change without notice. It is expressly understood and agreed that you assume and hereby expressly release us from all liability, in tort, contract or otherwise, incurred in connection with the use of our products, technical assistance, and information.

Any statement or recommendation not contained herein is unauthorized and shall not bind us. Nothing herein shall be construed as a recommendation to use any product in conflict with patents covering any material or its use. No license is implied or in fact granted under the claims of any patent.

Issue number: Buna CB VP PBR 4037 / Date of issue: June 07, 2010 / Information current as of date of issue. Please contact your LANXESS representative to determine if this publication has been revised.